

TEST REPORT TRANSLATION

CLIENT: **COMPOSITES GUREA, S.A.**

CONTACT PERSON: **FERNANDO ENCIO**

ADDRESS: **Zalain Auzoa, 13 – Apartado 1
31780 VERA DE BIDASOA (Navarra)**

TESTED MATERIAL: **HPL COMPACT LAMINATE SAMPLES
«PARKLEX FACADE “F” RUBI»
«PARKLEX FACADE “S” RUBI»**

PURPOSE OF THE REQUEST: **RESISTANCE TO ARTIFICIAL WEATHERING**

RECEIPT DATE **10.05.2007**
TEST BEGINNING DATE: **10.05.2007**
TEST END DATE: **21.02.2008**
REPORT EMISSION DATE **28.03.2008**

The results of the tests can only be applied to the material received and tested in this Research Centre on the indicated dates.

This report is in four (4) pages and it cannot be reproduced without CIDEMCO's authorisation, but in an unabridged version.



Arantxa Pérez
Analyst



Javier García Jaca
Head of Materials Department

1. TEST SPECIMENS

HPL compact laminate samples belonging to the company “**COMPOSITES GUREA, S.A.**” was received at CIDEMCO on May 10th of 2007 with the following references:

- «**PARKLEX FACADE “F” RUBI**»
- «**PARKLEX FACADE “S” RUBI**»

2. TEST REQUESTED

The requested test is the following:

- ◆ Weathering performance according to UNE-EN ISO 4892-2:2006 “Methods of exposure to laboratory light sources. Part 2: Xenon-arc sources”

3. CARRIED OUT TESTS

As indicated in the standard EN 438-2:2005 apt. 29 about the assessment of the properties of high pressure decorative laminates, the weathering test is carried out according to the method of the standard UNE-EN ISO 4892-2:2006.

◆ Weathering performance according to UNE-EN ISO 4892-2:2006

The test was carried out in a chamber with xenon arc lamp. This lamp fitted with suitable filters and properly maintained produces a radiation with a spectral energy distribution similar to that of terrestrial sunlight in the ultraviolet and visible regions of the spectrum. The used combination of filters is:

- Inside filter: Borosilicate
- Outside filter: Borosilicate

Chamber temperature: $(38 \pm 5)^{\circ}\text{C}$.

Relative humidity: $(65 \pm 5)\%$.

Black panel temperature: $(65 \pm 3)^{\circ}\text{C}$.

Spray cycle: - 18 minutes spray
- 102 minutes dry period

Test duration: Two assessment are made:

- After 325 MJ/m² of irradiance
- After 650 MJ/m² of irradiance

The degradation was evaluated using a grey scale (EN 20105-A02:1994) as reference. This scale uses the following values:

- EG=1 Very strong change
- EG=2 Strong change
- EG=3 Important change
- EG=4 Change beginning
- EG=5 Without change

The surface of the test specimen was observed by naked eye, at a distance of approximately 50 cm. The appearance was assessed in comparison with the control specimen with the following rating scale:

- Rating 5: No visible change
- Rating 4: Change of gloss only
- Rating 3: Hairline surface cracks and/or erosion of surface delamination
- Rating 2: Surface cracks
- Rating 1: Blistering and/or delamination

The samples are classified according to EN 438-6:2005 as:

Irradiance	Specification (EN 438-6:2005)	Classification
325 MJ/m ²	Grey scale EG=3	EGS or EGF
650 MJ/m ²	Appearance Rating 4	EDS or EDF

4. RESULTS

In the following table the obtained results are showed:

Reference	Performance (650 MJ/m ²)				
	No. hours	Appearance	Grey scale	Specification	Assessment
«PARKLEX FACADE “F” RUBI»	3000	Rating 5	4	Appearance Rating 4 Grey scale Rating 3	EDF
«PARKLEX FACADE “S” RUBI»	3000	Rating 5	4		EDS

The test sample continues in the test until the time required for the sample to receive an irradiance of 1080 MJ/m² is completed. The results obtained are shown in the following table:

Reference	Performance (1080 MJ/m ²)		
	No. hours	Appearance	Grey scale
«PARKLEX FACADE “F” RUBI»	5000	Rating 5	3
«PARKLEX FACADE “S” RUBI»	5000	Rating 5	3

Despite the sample has received double of the irradiance (1080 MJ/m²) specified in the Standard EN 438-6:2005; the value of the grey scale and the appearance of the test sample are into the specifications required when the irradiance is 650 MJ/m².